

SMITHSONIAN INSTITUTION.  
UNITED STATES NATIONAL MUSEUM.

W. F. FOSHAG  
Division of Mineralogy

THE CASAS GRANDES METEORITE.

BY

WIRT TASSIN,  
*Assistant Curator, Division of Mineralogy.*

---

From the Proceedings of the United States National Museum, Vol. XXV, pages 69-74  
(with Plates I-IV).

[No. 1277.]



WASHINGTON:  
GOVERNMENT PRINTING OFFICE.

1902.

SMITHSONIAN INSTITUTION.  
UNITED STATES NATIONAL MUSEUM.

---

THE CASAS GRANDES METEORITE.

BY

WIRT TASSIN,  
*Assistant Curator, Division of Mineralogy.*

---

From the Proceedings of the United States National Museum, Vol. XXV, pages 69-74  
(with Plates I-IV).

[No. 1277.]



WASHINGTON:  
GOVERNMENT PRINTING OFFICE.

1902.

## THE CASAS GRANDES METEORITE.

---

By WIRT TASSIN,

*Assistant Curator, Division of Mineralogy.*

---

### HISTORY.

One hundred and forty miles southwest of Juarez, or El Paso del Norte, in the State of Chihuahua, Mexico, are the ancient Mexican ruins variously known as Casa Grande, Casas Grandes, Montezuma Casas Grandes, and Casas Grandes de Malintzin, relics of a civilization that before the Spanish invasion occupied the country as far north as Santa Fe. In this ruin certain inhabitants of a small Mexican town, near to and which takes its name from the Casas Grandes ruins, discovered a roundish mass of meteoric iron.

The news of the discovery was published by Tarayre,<sup>1</sup> who reported that Müller, the director of the mint of Chihuahua, during the course of an exploration of the great temple of the Casas Grandes, brought to light a lenticular mass of meteoric iron 50 centimeters in diameter, carefully wrapped in cloths similar to those enshrouding the mummies in the ancient tombs of the same locality. Later, Mr. William M. Pierson, United States vice-consul at El Paso del Norte, gave a more circumstantial account of the find in a letter<sup>2</sup> to the State Department, from which the following is taken:

A party of these Mexican mountaineers, as a matter of curious speculation, commenced excavating in the old ruins of the Montezuma Casas Grandes, each man drifting into the old ruins at separate and several points. One, Teodoro Alverado, more fortunate than the others, drifted into a large room, in the middle of which there appeared a kind of tomb made of brick. Curiosity led this bold knight of the crowsbar to renew his excavations, and when he had reached the middle of this tomb, he there found this curious mass of meteoric iron \* \* \* carefully and curiously wrapped in a kind of coarse linen \* \* \* Angerstein, Leroy, and myself have made up the necessary funds to purchase this rare and novel specimen, making it a mutual adventure, and have started a large mercantile wagon, capable of carrying 10,000 pounds, to transport it to this city. Our intention is to secure it for the admiration of the curious and the lovers of science. We shall have it safely lodged in the consulate within fifteen days from this date.

---

<sup>1</sup> Archives de la Commission Scientifique du Mexique, Paris, III, 1867, p. 348.

<sup>2</sup> Smithsonian Report, 1873, p. 419.

The letter here cited was referred by the Assistant Secretary of State to the then Secretary of the Smithsonian Institution, Professor Henry, who took measures to secure the mass as indicated by the following extract from his reply:

It would give us great pleasure to subject a portion of the meteorite in question to an investigation in regard to its gaseous contents; and if the gentlemen who own it will present it to the Institution, we will cheerfully pay the expense of transportation.

Nothing further was heard from the mass until the centennial year, 1876, when the Institution became the possessor by gift of an uncut block of meteoric iron, purporting to be the Casas Grandes mass, exhibited among the Mexican minerals at the exposition.

#### DESCRIPTION.

This is a lenticular mass of iron measuring 97 by 74 by 46 centimeters (38 by 29 by 18 inches) and weighing before cutting 1,544.788 kilos (3,407 pounds). The outer surface of the mass is almost entirely covered with broad, shallow pittings, some of which, as shown in the plates, are quite large. This outer surface is more or less oxidized and in no way differs from the so-called "crust surface" of other meteoric irons containing little or no ferrous chloride.

A portion of the mass was cut for exchange and study purposes by means of a slotter. The iron machined readily and was no harder than ordinary mild steel, with about the same toughness as a low-grade nickel steel. The surface left by the tool measured 55 and 38 centimeters in the two longest diameters and was readily worked down with shop files of increasing fineness, and lastly polished with emery flour. The face thus obtained showed a few small scattered nodules and grains of troilite, the largest not over 2 centimeters in diameter and the smaller, and more numerous, not larger than a pin head. No schreibersite, carbonaceous nodules, or stony matter is visible on the polished surface. After exposure to the action of dilute nitric acid, the polished surface develops the beautiful crystalline structure shown in Plate III. Seen by reflected light, the etched surface shows numerous fine lines of a yellowish to tin white color which was found to be schreibersite. The schreibersite is in general lineally arranged and is usually only to be observed by reflected light, though occasionally it is so prominent as to stand in relief, as shown on the face of the cube here figured.

#### THE CHEMICAL COMPOSITION.

The turnings made by the "slotter" were cut into small pieces by means of snips and carefully washed in alcohol and ether to remove any grease or dirt that may have been present, and after thorough drying were bottled and sealed to prevent possible oxidation. A weighed amount (7.02 grams) of these washed clippings was dissolved

in aqua regia and evaporated to dryness on the water bath; concentrated hydrochloric acid was then added and the whole carefully heated until all the ferric oxide was dissolved and again brought to dryness. This operation was repeated until all the nitric acid was expelled. The residue was then dissolved in 15 cubic centimeters of hydrochloric acid, evaporated till the solution was almost sirupy, and then diluted to about 100 cubic centimeters with cold water and filtered, using the "double filter" method of J. Lawrence Smith.<sup>1</sup> This residue was examined and found to consist entirely of carbon. The filtrate and washings from the above were collected and made up to 1,000 cubic centimeters, and all the determinations were made in the same solution. The analysis gave:

Iron.....	95.13
Nickel.....	4.38
Cobalt.....	.27
Copper.....	trace.
Carbon.....	trace.
Phosphorus.....	.24

This corresponds to—

Nickeliferous iron.....	98.65
Schreibersite.....	1.35
	100.00

It will be observed that the analysis shows no sulphur and that the amount of carbon present was practically negligible. While it is evident that the carbon and sulphur contents would naturally vary, it was thought worth while to determine whether or not the nickel-cobalt contents were a constant or not. Accordingly successive samples, weighing as nearly as possible to 5 grams each, were put in solution and made up to a definite amount and portions containing the equivalent of 1 gram of substance taken and the nickel-cobalt contents determined by the acetate method. Each sample was treated as nearly alike as possible and the precipitation being repeated six times with each. It was found that while in certain cases the nickel-cobalt contents did not vary appreciably from the figures given above, in others the variation was considerable, and in one instance the cobalt was wanting entirely. Thus:

Constituents.	a	b	c
Nickel.....	4.38	5.02	4.50
Cobalt.....	.27	.30	.00

These figures show a wide variation in composition in different parts of a mass, the character of whose etch figures is such that it would be

<sup>1</sup>Original Researches, p. 312.

entirely in the graphitic condition. After weighing it was burned in a current of oxygen.

#### SILICATES AND OTHER MINERALS.

The only siliceous mineral observed was found coating a small portion of some schreibersite, and though large amounts of iron were treated for the purpose of securing more, none was found. The mineral was clear, colorless, and entirely without effect on polarized light, and not enough of it could be secured for analysis. No other minerals, such as rhabdite, cohenite, chromite, diamond, etc., were observed.



THE CASAS GRANDES METEORITE.



THE CASAS GRANDES METEORITE.





PORTION OF CASAS GRANDES MASS, ETCHED.



CUBE, ETCHED, OF CASAS GRANDES IRON.

The fine lines in relief are Schreibersite.

