

Nauma (b)
12/21/84

POINT 50 (50)

CA 278 SI 23278 MG 31196 FE 2887 BC 13913

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SI02	23278	413	58.95	56.24	0.43	SI	2.010	82.7	16.2	1.1	
FED	2887	50	10.74	10.76	0.22	FE	0.322				
MGO	31196	107	30.41	30.75	0.18	MG	1.638	Z	2.010	X	1.981
CA0	278	8	0.55	0.56	0.03	CA	0.021	AL4	0.000	AL6	0.000
3		TOTAL	100.64	98.32			3.990				

POINT 51 (51)

CA 318 SI 23507 MG 32474 FE 2792 BC 13964

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23507	415	59.31	56.65	0.43	SI	1.999	83.5	15.3	1.2	
FED	2792	49	10.34	10.37	0.21	FE	0.306				
MGO	32474	111	31.55	31.79	0.18	MG	1.672	Z	1.999	X	2.002
CAD	318	9	0.63	0.64	0.04	CA	0.024	AL4	0.000	AL6	0.000
3		TOTAL	101.84	99.46			4.001				

#

POINT 52 (52)

CA 43 SI 16055 MG 43408 FE 4546 BC 13974

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	FD	FA
SID2	16055	283	40.44	40.28	0.34	SI	1.009	82.2	17.8	
FED	4546	79	16.96	16.85	0.28	FE	0.353			
MGO	43408	149	42.23	43.65	0.21	MG	1.629	Z	1.009	X 1.983
CAD	43	1	0.02	0.02*	0.01	CA	0.001			
3		TOTAL	99.65	100.79			2.991			

#

POINT 53 (53)

CA 54 SI 16143 MG 43637 FE 4525 BC 13994

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	FD	FA
SID2	16143	284	40.60	40.43	0.34	SI	1.010	82.3	17.7	
FED	4525	79	16.86	16.75	0.28	FE	0.350			
MGO	43637	149	42.40	43.78	0.21	MG	1.630	Z	1.010	X 1.981
CAD	54	1	0.05	0.05	0.01	CA	0.001			
3		TOTAL	99.90	101.01			2.990			

#

POINT 54 (54)

CA 301 SI 23442 MG 32269 FE 2857 BC 13986

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23442	413	59.06	56.41	0.43	SI	1.998	83.2	15.7	1.1	
FED	2857	50	10.57	10.60	0.21	FE	0.314				
MGO	32269	110	31.30	31.59	0.18	MG	1.667	Z	1.998	X	2.004
CAD	301	9	0.59	0.60	0.03	CA	0.023	AL4	0.000	AL6	0.000
3		TOTAL	101.52	99.20			4.002				

#

POINT 55 (55)

CA 275 SI 23432 MG 32714 FE 2860 BC 13989

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23432	413	59.02	56.42	0.43	SI	1.991	83.5	15.5	1.0	
FED	2860	50	10.58	10.61	0.21	FE	0.313				
MGO	32714	112	31.72	32.00	0.18	MG	1.684	Z	1.991	X	2.017
CAD	275	8	0.54	0.55	0.03	CA	0.021	AL4	0.000	AL6	0.000
3		TOTAL	101.86	99.58			4.009				

#

POINT 56 (56)

CA 39 SI 16004 MG 43938 FE 4360 BC 13990

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	FD	FA	
SID2	16004	282	40.26	40.12	0.34	SI	1.008	82.9	17.1		
FED	4360	76	16.24	16.14	0.27	FE	0.339				
MGO	43938	150	42.70	43.96	0.22	MG	1.645	Z	1.008	X	1.985
CAD	39	1	0.01	0.01*	0.01	CA	0.000				
3		TOTAL	99.22	100.24			2.992				

#

POINT 57 (57)

CA 52 SI 16035 MG 44051 FE 4469 BC 13993

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	FD	FA	
SID2	16035	282	40.33	40.20	0.34	SI	1.005	82.6	17.4		
FED	4469	78	16.65	16.54	0.28	FE	0.346				
MGO	44051	151	42.81	44.14	0.22	MG	1.644	Z	1.005	X	1.991
CAD	52	1	0.04	0.04	0.01	CA	0.001				
3		TOTAL	99.83	100.92			2.995				

#

POINT 58 (58)

CA 278 SI 23275 MG 31795 FE 2970 BC 13997

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23275	410	58.59	55.97	0.42	SI	1.996	82.6	16.4	1.1	
FED	2970	52	10.99	11.01	0.22	FE	0.328				
MGO	31795	109	30.81	31.18	0.18	MG	1.658	Z	1.996	X	2.007
CAD	278	8	0.54	0.55	0.03	CA	0.021	AL4	0.000	AL6	0.000
3		TOTAL	100.93	98.72			4.004				

#

POINT 59 (59)

CA 50 SI 15994 MG 43731 FE 4412 BC 13999

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	15994	282	40.21	40.06	0.34	SI	1.007	82.7	17.3		
FED	4412	77	16.42	16.33	0.28	FE	0.343				
MGD	43731	150	42.47	43.78	0.21	MG	1.641	Z	1.007	X	1.985
CAD	50	1	0.04	0.04*	0.01	CA	0.001				
3		TOTAL	99.15	100.20			2.993				

#

POINT 60 (60)

CA 301 SI 23620 MG 31730 FE 2832 BC 14004

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23620	416	59.43	56.69	0.43	SI	2.012	83.1	15.8	1.2	
FED	2832	49	10.46	10.49	0.21	FE	0.311				
MGD	31730	108	30.73	31.01	0.18	MG	1.641	Z	2.012	X	1.975
CAD	301	9	0.59	0.60	0.03	CA	0.023	AL4	0.000	AL6	0.000
3		TOTAL	101.21	98.80			3.988				

#

POINT 61 (61)

CA 244 SI 23730 MG 32011 FE 2867 BC 14005

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23730	418	59.70	56.97	0.43	SI	2.011	83.2	15.8	0.9	
FED	2867	50	10.59	10.62	0.21	FE	0.313				
MGD	32011	109	31.00	31.29	0.18	MG	1.646	Z	2.011	X	1.978
CAD	244	7	0.47	0.48	0.03	CA	0.018	AL4	0.000	AL6	0.000
3		TOTAL	101.76	99.37			3.989				

#

POINT 62 (62)

CA 237 SI 23431 MG 32704 FE 2810 BC 14004

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23431	413	58.95	56.35	0.43	SI	1.995	83.8	15.3	0.9	
FED	2810	49	10.38	10.41	0.21	FE	0.308				
MGD	32704	112	31.68	31.92	0.18	MG	1.684	Z	1.995	X	2.010
CAD	237	7	0.45	0.46	0.03	CA	0.017	AL4	0.000	AL6	0.000
3		TOTAL	101.46	99.15			4.005				

#

POINT 63 (63)

CA 268 SI 23722 MG 32439 FE 2878 BC 14006

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23722	418	59.68	56.99	0.43	SI	2.003	83.3	15.7	1.0	
FED	2878	50	10.63	10.66	0.21	FE	0.313				
MGD	32439	111	31.42	31.71	0.18	MG	1.661	Z	2.003	X	1.994
CAD	268	8	0.52	0.53	0.03	CA	0.020	AL4	0.000	AL6	0.000
3		TOTAL	102.25	99.89			3.997				

#

POINT 63 (63)
CA 268 SI 23722 MG 32439 FE 2878 BC 14006

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23722	418	59.68	56.99	0.43	SI	2.003	83.3	15.7	1.0	
FED	2878	50	10.63	10.66	0.21	FE	0.313				
MGO	32439	111	31.42	31.71	0.18	MG	1.661	Z	2.003	X	1.994
CAO	268	8	0.52	0.53	0.03	CA	0.020	AL4	0.000	AL6	0.000
3		TOTAL	102.25	99.89			3.997				

#

POINT 64 (64)
CA 35 SI 15799 MG 43209 FE 4644 BC 14010

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	FD	FA	
SID2	15799	278	39.69	39.56	0.34	SI	1.000	81.9	18.1		
FED	4644	81	17.29	17.16	0.28	FE	0.363				
MGO	43209	148	41.93	43.44	0.21	MG	1.637	Z	1.000	X	2.000
CAO	35	1	0.01	0.01*	0.00	CA	0.000				
3		TOTAL	98.91	100.16			3.000				

#

POINT 65 (65)
CA 681 SI 22855 MG 30274 FE 2841 BC 14004

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	22855	402	57.50	54.79	0.42	SI	2.002	81.0	16.1	2.9	
FED	2841	49	10.50	10.52	0.21	FE	0.321				
MGO	30274	103	29.31	29.68	0.17	MG	1.617	Z	2.002	X	1.995
CAO	681	20	1.43	1.46	0.05	CA	0.057	AL4	0.000	AL6	0.000
3		TOTAL	98.74	96.45			3.998				

#

POINT 66 (66)
CA 267 SI 23365 MG 32392 FE 2883 BC 14005

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	EN	FS	WD
SID2	23365	411	58.78	56.18	0.43	SI	1.994	83.3	15.7	1.0	
FED	2883	50	10.65	10.68	0.21	FE	0.317				
MGO	32392	111	31.37	31.68	0.18	MG	1.675	Z	1.994	X	2.012
CAO	267	8	0.52	0.53	0.03	CA	0.020	AL4	0.000	AL6	0.000
3		TOTAL	101.33	99.06			4.006				

#

POINT 67 (67)
CA 36 SI 16190 MG 43047 FE 4518 BC 14011

	COUNTS	PEAK/BG	UNC	WT%	BACORR	WT%	SD	SF	FD	FA	
SID2	16190	285	40.67	40.47	0.34	SI	1.017	82.2	17.8		
FED	4518	79	16.81	16.70	0.28	FE	0.351				
MGO	43047	147	41.77	43.16	0.21	MG	1.616	Z	1.017	X	1.967
CAO	36	1	0.01	0.01*	0.00	CA	0.000				
3		TOTAL	99.26	100.34			2.983				

#